

# gloveon Alexa



## Nitrile Exam Gloves Powder Free, Gauntlet Cuff

GloveOn® Alexa is the bold and powerful new addition to our nitrile glove range, a tougher and stronger solution for workers in the healthcare sector. Distinguished by its gauntlet cuff that extends 500mm, GloveOn® Alexa is the glove of choice for maternity nurses assisting with water births, veterinarians, life science workers and room technicians responsible for cleaning surgical equipment.



### GloveOn® Alexa

GloveOn® Alexa		
<b>Length (mm)</b>	≥ 500	
<b>Thickness Measurements (mm)</b>		
Palm (centre of Palm)	0.17 ± 0.02	
Finger (15mm ± 3mm from tip)	0.21 ± 0.02	
<b>Physical Properties</b>	<b>Before Ageing</b>	<b>After Ageing</b>
Tensile Strength (MPa)	≥ 18	≥ 17
Elongation (%)	≥ 500	≥ 400
<b>Inspection Levels &amp; AQL</b>	<b>Inspection Level</b>	<b>AQL</b>
Watertightness	G1	1.5
Physical Dimensions	S2	4.0
Tensile Strength	S2	4.0
Visual Inspection (Major)	S4	2.5
Visual Inspection (Minor)	S4	4.0
Particulate Residue	N = 5	≤ 2mg/glove

### REORDER CODE

NTR90SS	SMALL
NTR90MM	MEDIUM
NTR90LL	LARGE

### FEATURES

- Palm textured
- Powder free
- Not made from natural rubber latex
- Chemo drugs tested
- Ambidextrous
- Gauntlet cuff
- Maya blue colour

### PACKAGING

50 gloves per box for S to L  
6 boxes per carton

### REGULATORY COMPLIANCE

ARTG 300229, MDD 93/42/EEC

### STANDARDS

AS/NZS 4011-1, ASTM D6978, ASTM F739, EN 374 part 2 & 3, EN 388, EN 420, EN 455 part 1, 2 & 3, EN 1186, EN 13130, CEN/TS 14234, ISO 10993 part 5 & 10, HACCP Certified

### MANUFACTURING ACCREDITATIONS

ISO 9001, ISO 13485

Chemotherapy Drugs and Concentration  
(Tested for Resistance to Permeation by Chemotherapy  
Drugs as per ASTM D6978-05-Test Report PN 133360)

Minimum Breakthrough  
Detection Time (minutes)

Carmustine (BCNU), 3.3mg/ml (3,300 ppm)	24.0 minutes
Cisplatin, 1.0mg/ml (1,000 ppm)	>240 minutes
Cyclophosphamide (Cytoxan), 20.0mg/ml (20,000 ppm)	>240 minutes
Dacarbazine (DTIC), 10.0mg/ml (10,000 ppm)	>240 minutes
Doxorubicin Hydrochloride, 2.0mg/ml (2,000 ppm)	>240 minutes
Etoposide (Toposar), 20.00mg/ml (20,000 ppm)	>240 minutes
Fluorouracil, 50.0mg/ml (50,000 ppm)	>240 minutes
Methotrexate, 25.0mg/ml (25,000 ppm)	>240 minutes
Mitomycin C, 0.5mg/ml (500 ppm)	>240 minutes
Paclitaxel (Taxol), 6.0mg/ml (6,000 ppm)	>240 minutes
Thiotepa, 10.0mg/ml (10,000 ppm)	56.9 minutes
Vincristine Sulfate, 1.0mg/ml (1,000 ppm)	>240 minutes

**WARNING:** Carmustine and Thiotepa, at the tested concentration, degraded nitrile glove at 24.0 minutes and 56.9 minutes, respectively. The safe use of gloves in chemotherapy treatment is solely the decision of clinicians authorised to make such decision.

A brand by

**D.MUN**

**Mun Australia**  
Toll free: 1800 456 837  
munglobal.com.au

**Birthing Kit  
Foundation**  
Australia  
Proud Supporter of  
Birthing Kit Foundation (Australia)

 Protection Always On

MKG2019-068