



Polyisoprene Surgical Gloves Powder Free, Under Glove

Designed to alert you of a puncture when partnered with GloveOn® Victor, our polyisoprene surgical under glove provides the ultimate protection for surgeons. Its blue colour has been specially selected to ensure that any punctures in the outer glove are detected quickly. Recommended for use in all surgical procedures that need good grip and dexterity whilst double gloving.



EN ISO 374-5



Tested in accordance with EN ISO 374-5
Resistance to Bacteria and Fungi - pass
Resistance to Viruses - pass

EN 421



Protection against
particulate radioactive
contamination
(Excluding Clause 4.3)

Physical Dimensions

| | |
|---|-------------|
| Length (mm) | 290 ± 10 |
| Cuff Thickness (25mm from cuff edge) (mm) | 0.15 ± 0.04 |
| Palm Thickness (Centre of palm) (mm) | 0.19 ± 0.04 |
| Finger Thickness (13mm ± 3mm from tip) (mm) | 0.21 ± 0.04 |

Physical Properties

| | Before Ageing | After Ageing |
|--------------------------------|---------------|--------------|
| | AS/NZS 4179 | AS/NZS 4179 |
| Force at break (N) | ≥ 12.5 | ≥ 9.5 |
| Elongation at break (%) | ≥ 700 | ≥ 550 |
| Modulus at 300% elongation (N) | ≤ 2.0 | - |

Performance Requirements

| | Inspection Level | AQL |
|---------------------------|------------------|-------------------|
| Watertightness | G1 | 0.65 |
| Physical Dimensions | S2 | 4.0 |
| Physical Properties | S2 | 4.0 |
| Visual Inspection (Major) | S4 | 2.5 |
| Visual Inspection (Minor) | S4 | 4.0 |
| Particulate Residue | N=5 | ≤ 2mg/glove |
| Seal Strength | N=20 | ≥ 1.2 N |
| Dye Penetration Test | N=20 | Accept 0 Reject 1 |

REORDER CODE

| | |
|---------|----------|
| SPI2255 | Size 5.5 |
| SPI2260 | Size 6.0 |
| SPI2265 | Size 6.5 |
| SPI2270 | Size 7.0 |
| SPI2275 | Size 7.5 |
| SPI2280 | Size 8.0 |
| SPI2285 | Size 8.5 |
| SPI2290 | Size 9.0 |

FEATURES

- Powder free
- Not made with natural rubber latex
- Textured
- Curved fingers
- Hand specific
- Distinctive blue glove color
- Sterilised using gamma irradiation

PACKAGING

1 pair per pouch
50 pairs per box
4 boxes per carton

REGULATORY COMPLIANCE

ARTG 439511, FDA 510 (k), EU 2016/425, MDR 2017/745

STANDARDS

AS/NZS 4179, ASTM D3577, ASTM D5151, ASTM D6124, ASTM D6978, ASTM D7102, ASTM F1671, ASTM D5712, EN 16523-1, EN 455 part 1, 2, 3 & 4, EN ISO 21420, EN ISO 374 part 1, 2, 4 & 5, ISO 11137, ISO 10282, ISO 10993 part 5 & 10

MANUFACTURING ACCREDITATIONS

ISO 9001, ISO 13485, EN ISO 13485

| Chemical | EN 16523-1 Permeation Level | EN ISO 374-4 Mean Degradation (%) |
|-------------------------|-----------------------------|-----------------------------------|
| K 40% Sodium Hydroxide | 6 | -41.9 |
| M 65% Nitric Acid | 5 | 34.9 |
| P 30% Hydrogen Peroxide | 6 | 19.0 |
| T 37% Formaldehyde | 6 | -41.6 |

| Measured breakthrough time (minutes) | >10 | >30 | >60 | >120 | >240 | >480 |
|--------------------------------------|-----|-----|-----|------|------|------|
| Permeation performance level | 1 | 2 | 3 | 4 | 5 | 6 |

Product disclaimer - <https://munglobal.com/product-disclaimer/>

A brand by



Mun Australia
Toll free: 1800 456 837
munglobal.com.au



Birthing Kit Foundation
Australia
Proud Supporter of
Birthing Kit Foundation (Australia)



Protection Always On